

Fábrica de Tintas Isolaca, Lda.

Rua Narciso Machado, 12
Zona Industrial da Maia I, Sector X
4475-250 Maia (PT)
Telefone: + 351 22 943 87 50
Email: isolaca@isolaca.com

Technical Data Sheet

FTPP93837-4

Page 1 of 1

PP93837	PU WHITE BASE COAT
---------	--------------------

CHARACTERISTICS:

Polyurethane base coat recommended for high-quality lacquering, featuring suitable resistance for high-gloss finishes, good filling, easy sanding, and fast drying.

TECHNICAL SUPPLY DATA: 1)

Viscosity:..... 2400±500 cP S3, 30rpm (23°C)
Theoretical density:..... 1.494 Kg/L (23°C)

TECHNICAL APPLICATION DATA: 1)

Application:..... Airless/Airmix
Mixing Ratio (Volume):..... 2:1
Application Viscosity:..... 18-20 " FORD 4 (23°C)
Component:..... CP33491
Solid content (mixture) (±1):..... 63.2%
Dilution:..... 0-3%
Drying Time:..... 3 h
Pot-Life:..... 2 h

To adjust the viscosity, our diluents should be used: DP2689, DP2695, DP94037.

The storage must be made with properly sealed containers and in cool places. The expiration date is 12 months.

The surfaces to be applied must be thoroughly cleaned and free from moisture.

1) Provisional values

This information gives a general idea of the main characteristics and application of the product, may therefore have to be adapted to the conditions in use of the product.

Our technical services are fully available for further clarification and suggestions.

Following a policy of continuous improvement, we reserve the right to change specifications without notice.

* value for guidance