

**Fábrica de Tintas Isolaca, Lda.**

Rua Narciso Machado, 12  
Zona Industrial da Maia I, Sector X  
4475-250 Maia (PT)  
Telephone: + 351 22 943 87 50  
Email: isolaca@isolaca.com

## Technical Data Sheet

FTVP53100-2

Page 1 of 1

VP53100	PU CLEAR TOP COAT (HIGH GLOSS)
---------	--------------------------------

CHARACTERISTICS:

High gloss finishing top coat with good filling and excellent leveling. Top coat can be polished/sanded after 24 to 36 hours of its application.

TECHNICAL SUPPLY DATA:

Viscosity:..... 160±15 " FORD 4 (23°C)  
Theoretical density:..... 1.039 Kg/L (23°C)

TECHNICAL APPLICATION DATA:

Application:.....	Airless/Airmix	
Mixing Ratio (Volume):.....	1:1	
Application Viscosity:.....	15-18	" FORD 4 (23°C)
Gloss* (60°):.....	90	
Component:.....	CP56410	CP56500
Solid content (mixture) (±1):.....	45.9%	45.8%
Dilution:.....	5-11%	9-15%
Drying Time:.....	8 h	8h
Pot-Life: .....	>6 h	>6 h

To adjust the viscosity, our diluents should be used: DP2689, DP2695, DP94037.

The storage must be made with properly sealed containers and in cool places. The expiration date is 12 months.

The surfaces to be applied must be thoroughly cleaned and free from moisture.

This information gives a general idea of the main characteristics and application of the product, may therefore have to be adapted to the conditions in use of the product.

Our technical services are fully available for further clarification and suggestions.

Following a policy of continuous improvement, we reserve the right to change specifications without notice.

\* value for guidance