

Fábrica de Tintas Isolaca, Lda.

Rua Narciso Machado, 12
Zona Industrial da Maia I, Sector X
4475-250 Maia (PT)
Telefone: + 351 22 943 87 50
Email: isolaca@isolaca.com

Technical Data Sheet

FTIO93460-2

Page 1 of 1

IO93460	PU INSULATOR
---------	--------------

CHARACTERISTICS:

Polyurethane wood or MDF sealer with high transparency and hardness, providing better insulation and finish for the subsequent products to be applied.

TECHNICAL SUPPLY DATA: 1)

Viscosity:..... 10±2 " FORD 4 (23°C)
Theoretical density:..... 0.904 Kg/L (23°C)

TECHNICAL APPLICATION DATA: 1)

Application:..... Airmix
Mixing Ratio (Volume):..... 1:1
Application Viscosity:..... 8-12 " FORD 4 (23°C)
Component:..... CP36151
Solid content (mixture) (±1):..... 23.1%
Dilution:..... 0%
Drying Time:..... >4 h
Pot-Life:..... >6 h

The storage must be made with properly sealed containers and in cool places. The expiration date is 12 months.

The surfaces to be applied must be thoroughly cleaned and free from moisture.

1) Provisional values

This information gives a general idea of the main characteristics and application of the product, may therefore have to be adapted to the conditions in use of the product.

Our technical services are fully available for further clarification and suggestions.

Following a policy of continuous improvement, we reserve the right to change specifications without notice.

* value for guidance